

# Specification Sheet

GHTT-4001

High-Performance Plastic Optical Fiber

E s k a™

**MITSUBISHI RAYON CO.,LTD.**

ESKA OPTICAL FIBER DIVISION

6-41 Konan 1-Chome,Minato-ku,Tokyo,JAPAN

Phone : +81-3-5495-3060

Facsimile : +81-3-5495-3212


1. Scope  
This specification covers basic requirements for the structure and optical performances of GHTT-4001.
2. Structure

Table 1

GHTT-4001

Item		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber	Core Material	-	Polymethyl-Methacrylate Resin		
	Cladding Material	-	Fluorinated Polymer		
	Core Refractive Index	-	1.49		
	Refractive Index Profile	-	Step Index		
	Numerical Aperture	-	0.5		
	Core Diameter	μm	920	980	1,040
	Cladding Diameter	μm	940	1,000	1,060
Jacket	Material	-	Polyethylene		
	Color	-	Black		
	Dimension	mm	2.13	2.20	2.27
Number of cords		-	1		
Strength Member	Material	-	Aramid Fiber		
Sheath	Material	-	Poly-Vinyl-Chloride		
	Color	-	Gray		
	Diameter	mm	4.8	5.0	5.2
Approximate Weight		g/m	27		
Indication on the Jacket		-	·····ESKA PREMIER·····;Pink		

### Sectional View



## 3. Performances

Table 2

		GHTT-4001				
Item		Acceptance Criterion and/or [ Test Condition ]	Specification			
			Unit	Min.	Typ.	Max.
Maximum Rating	Storage Temperature	No Physical Deterioration [ in a Dry Atmosphere ]		-40	-	+85
	Operation Temperature	No Deterioration in Optical Properties* [ in a Dry Atmosphere ]		-40	-	+85
		No Deterioration in Optical Properties** [ under 95%RH condition ]		-	-	+75
Optical Properties	Transmission Loss [ 650nm Collimated Light ]	[ 25 50%RH ]	dB/km	-	-	170
		[ Operation Temperature ]	dB/km	-	-	190
Mechanical Characteristics	Minimum Bend Radius	Loss Increment 0.5dB [ A Quarter Bend ]	mm	40	-	-
	Repeated Bending Endurance	Loss Increment 1dB [ in Conformity to the JIS C 6861 ]***	Times	5,000	-	-
	Tensile Strength	Tensile Force at 5% Elongation; in Conformity to the JIS C 6861 ]	N	245	-	-
	Twisting Endurance	Loss Increment 1dB [ Sample Length : 1m Tensile Force : 4.9N ]	Times	5	-	-
	Impact Endurance	Loss Increment 1dB [ in Conformity to the JIS C 6861 ]	N·m	-	-	-

All tests are carried out under temperature of 25 unless otherwise specified.

\* Attenuation change shall be within +/- 10% after 1,000 hours.

\*\* Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

\*\*\* Bend Angle +/-90° ,Bend Radius 15mm,Tension 500g